

CLAIMS

1. A method for manufacturing a thermoplastic resin vessel, in which a cup-shaped vessel is thermally
5 formed from a thermoplastic resin sheet by a plug, the method comprising the steps of:

pre-forming the thermoplastic resin sheet by the plug; and next clamping the pre-formed portion of the thermoplastic resin sheet to accomplish the forming.

10 2. The method for manufacturing the thermoplastic resin vessel according to claim 1, wherein the pre-forming step comprises the steps of: fixing a formed portion outer periphery of the thermoplastic resin
15 sheet.

3. The method for manufacturing the thermoplastic resin vessel according to claim 1, wherein the pre-forming step comprises the steps of: drawing a
20 portion corresponding to an orifice portion or a flange portion of the cup-shaped vessel.

4. The method for manufacturing the thermoplastic resin vessel according to claim 2, wherein
25 the pre-forming step comprises the steps of: drawing a portion corresponding to an orifice portion or a flange portion of the cup-shaped vessel.

5. The method for manufacturing the
30 thermoplastic resin vessel according to claim 3, wherein

the clamping step comprises the steps of: extruding a part of a resin in the portion corresponding to the flange portion in flange inner and outer peripheral directions; and forming the flange portion.

5

6. The method for manufacturing the thermoplastic resin vessel according to claim 4, wherein the clamping step comprises the steps of: extruding a part of a resin in the portion corresponding to the flange portion in flange inner and outer peripheral directions; and forming the flange portion.

10

7. The method for manufacturing the thermoplastic resin vessel according to claim 3, further comprising the steps of: applying a lubricant to at least a portion of the thermoplastic resin sheet corresponding to the flange portion.

15

8. The method for manufacturing the thermoplastic resin vessel according to claim 4, further comprising the steps of: applying a lubricant to at least a portion of the thermoplastic resin sheet corresponding to the flange portion.

20

9. The method for manufacturing the thermoplastic resin vessel according to claim 5, further comprising the steps of: applying a lubricant to at least a portion of the thermoplastic resin sheet corresponding to the flange portion.

25

30

10. The method for manufacturing the thermoplastic resin vessel according to claim 6, further comprising the steps of: applying a lubricant to at least a portion of the thermoplastic resin sheet corresponding to the flange portion.

11. The method for manufacturing the thermoplastic resin vessel according to claim 1 or 2, wherein the thermoplastic resin sheet is formed of at least a thermoplastic polyester resin.

12. The method for manufacturing the thermoplastic resin vessel according to claim 1 or 2, wherein the thermal forming step comprises a forming method comprising the steps of:

pneumatically forming the thermoplastic resin sheet into a shape of a lower mold heated at not less than a crystallization temperature of the thermoplastic resin sheet, and thermally fixing the sheet; and thereafter decompressing the inside of a formed article to contract the formed article, forming the article into a shape of the plug which is a final vessel shape, and cooling the article.

13. The method for manufacturing the thermoplastic resin vessel according to claim 1 or 2, further comprising the steps of: forming the sheet in such a manner that a height (H)/orifice portion inner diameter (D) of the thermoplastic resin vessel is in a range of 1.3 to 2.1.

14. The method for manufacturing the thermoplastic resin vessel according to claim 1 or 2, further comprising the steps of: forming the sheet in such a manner that an area drawing magnification of a bottom part of the thermoplastic resin vessel is in a range of 3.5 to 10 times.